

High-Temperature Analysis of Polyether Sulfone

Application Note

Materials Testing and Research, Polymers

Author

Graham Cleaver
Agilent Technologies, Inc.

Introduction

Elevated temperature is preferred for the analysis of polyether sulfones to reduce operating pressure and improve resolution by reducing solvent viscosity. This particular sample was readily soluble in DMF at room temperature. Agilent PLgel 5 μm MIXED-C columns are well suited to the analysis of polyether sulfones.



PLgel 5 μm MIXED-c columns are designed for rapid polymer analysis. With its linear calibration up to 2 million MW, this is the column of choice for highest resolution and accuracy in molecular weight distribution analyses. Rapid solvent change capability, excellent temperature stability and the high resolution of the PLgel 5 μm MIXED-C also provide the versatility essential for today's R&D laboratory.

Conditions

| | |
|--------------|---|
| Columns: | 2 x PLgel 5 μm MIXED-C, 300 x 7.5 mm (part number PL1110-6500) |
| Eluent: | DMF + 0.1% LiBr |
| Flow Rate: | 1.0 mL/min |
| Temperature: | 60 °C |
| Detection: | 390-MDS Multi Detector Suite (differential refractive index) |




Figure 1. Analysis of polyether sulfone using PLgel 5 μm MIXED-C columns

www.agilent.com/chem

This information is subject to change without notice.

© Agilent Technologies, Inc. 2015

Published in UK, April 30, 2015

5991-5811EN



Agilent Technologies